

ABSTRACT

A glass comprising in mole percent based on oxide:

SiO ₂	55-70
PbO	30-38
Na ₂ O	>0-4.5
K ₂ O	0-2.5

and essentially free of TiO₂.

JER:\BART\CLIENTS\SGT35\PATENT APPLICATION.DOC